



# GITICOVER 11040

GITI ASSA Co.

<b>Product Description</b>	Two-pack polyamide cured epoxy primer which contains zinc phosphate pigments to protect all internal and external blasted steel from corrosion. It cures to a strong and highly rust preventing coat.
<b>Recommended Use</b>	As a general purpose primer for use under two component epoxy coatings such as GITICOVER system on all types of blasted steel where appropriate protective coating can be done immediately after abrasive blast cleaning.

## Physical Properties

<b>Finish and Color</b>	Flat, Red Brown, Grey			
<b>Drying Time</b>	Substrate Temperature	10 °C	25 °C	35 °C
	Set to touch <sup>1</sup>	1.5 h	1 h	30 min
	Dry through <sup>1</sup>	24 h	8 h	2 h
<sup>1</sup> Drying times are generally related to film thickness, air circulation, humidity, temperature, and number of coats, and will be affected correspondingly.				
<b>Solids By Volume</b>	52±2 % (Determined by ISO 3233)			
<b>Theoretical Spreading Rate</b>	10.4 m <sup>2</sup> /L in 50 µm DFT.			
<b>Specific Gravity</b>	1.50±0.05 for mixture of Base and Curing agent.			
<b>Flash Point</b>	Base: 18°C (Closed Cup) Curing agent: 17°C (Closed Cup)			

## Application Details

<b>Surface Preparation</b>	Remove oil, grease, dirt and any other contaminants from the surface. The surface should be assessed and treated in accordance with ISO 8504. * Bare steel: Blast cleaning to Sa2.5 or power tool cleaning to St3.0 (ISO 8501-1:2007). Roughness: using suitable abrasive to achieve 50 ~ 75 µm (ISO 8503-2).
<b>Application Conditions</b>	The Surface should be clean and dry completely; The surface temperature should be min. 5 °C and at least 3 °C above the dew point of the air. In the confined spaces, provide adequate ventilation during application and drying.
<b>Mixing</b>	Base (Part A) : Curing Agent (Part B) = 6.5:1 (by weight) Mix thoroughly together prior to application in the properties with power agitator.
<b>Pot Life</b>	8 h at 25 °C
<b>Thinning</b>	Thinner No. 3010 Do not dilute each components separately, only the mixture.
<b>Application Method</b>	Spray (Airless or Air), Roller or Brush application For airless spray application: Nozzle orifice : 0.017 ~ 0.019" Output pressure : 2100 ~ 2400 psi Spray angle : 40 ~ 60 ° (Airless spray data are indicative and subject to adjustment)
<b>Typical Film Thickness</b>	50~75 µm DFT May be specified in another film thickness than indicated depending on purpose and area of use.



## **GITICOVER 11040**

**GITI ASSA Co.**

<b>Recoating Interval</b>	At 25 °C	Minimum : 16 h				
		Maximum : 21 d				
	The surface should be dry and free from any contamination prior to application of the subsequent coat.					
<b>Subsequent Coat</b>	GITICOVER 23101, 23121, 24121, 23107, 23127, GITIMASTIC 43191, 52141, 51161, GITIGUARD 22121					
<b>Shelf Life</b>	18 months in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.					
<b>Heat Resistance</b>	Continuous	: 90 °C (Non-immersion service)				
	Non-continuous	: 120 °C (Non-immersion service)				
<b>Chemical Resistance</b>		Acids	Alkalis	Solvents	Salts	Water
	Splash & Spillage	Good	Good	Good	Excellent	Excellent
	Fumes	Very Good	Very Good	Very Good	Excellent	Excellent
	Immersion	Fair	Good	Fair	Good	Good
<b>Standard Packing Unit</b>	20.8 kg base , 3.2 kg GITICURE 10050					
<b>Health and safety</b>	Do not store at temperature below 10 °C or above 30 °C. Protect skin and eyes from direct contact with liquid paint, and avoid prolonged breathing of solvent vapors. Use with adequate ventilation. Respiratory protection is recommended when applying this product in confined spaces or stagnant air.					
<b>Rev.06</b>	Mar. 2019					