



# GITIGUARD 31111

GITI ASSA Co.

<b>Product Description</b>	Two-pack polyamide cured food grade epoxy based high- build finish coat designed for potable water services. It may be used in contact with food products and for fresh water tank.
<b>Recommended Use</b>	As a finish coat for fresh water piping, tanks and swimming pools.

## Physical Properties

<b>Finish and Color</b>	Gloss, White			
<b>Drying Time</b>	Substrate Temperature	10 °C	25 °C	35 °C
	Set to touch <sup>1</sup>	2.5 h	2 h	1 h
	Dry through <sup>1</sup>	48 h	8 h	2 h
<sup>1</sup> Drying times are generally related to film thickness, air circulation, humidity, temperature, and number of coats, and will be affected correspondingly.				
<b>Solids By Volume</b>	54±2 % (Determined by ISO 3233)			
<b>Theoretical Spreading Rate</b>	7.2 m <sup>2</sup> /L in 75 µm DFT			
<b>Specific Gravity</b>	1.35±0.05 for mixture of Base and Curing agent.			
<b>Flash Point</b>	Base: 21°C (Closed Cup) Curing agent: 17°C (Closed Cup)			

## Application Details

<b>Surface Preparation</b>	Remove any oil, grease, dirt and any other contaminants from the surface before painting by proper method such as solvent cleaning and fresh water washing, etc.
<b>Application Conditions</b>	The Surface should be clean and dry completely; The surface temperature should be min. 5 °C and at least 3 °C above the dew point of the air. In the confined spaces, provide adequate ventilation during application and drying.
<b>Mixing</b>	Base (Part A) : Curing Agent (Part B) = 4 : 1 (by weight) Mix thoroughly together prior to application in the properties with power agitator.
<b>Pot Life</b>	8 h at 25 °C
<b>Preceding Coat</b>	GITIGUARD 11140, 22121 in potable water piping and tanks.
<b>Thinning</b>	Thinner No.3010 Do not dilute each component separately, only the mixture.
<b>Application Method</b>	Spray (Airless or Air), Roller or Brush application For airless spray application: Nozzle orifice : 0.017 ~ 0.019" Output pressure : 1800 ~ 2700 psi Spray angle : 40~60° (Airless spray data are indicative and subject to adjustment)
<b>Typical Film Thickness</b>	75 µm DFT May be specified in another film thickness than indicated depending on purpose and area of use.



## **GITIGUARD 31111**

**GITI ASSA Co.**

<b>Recoating Interval</b>	At 25 °C	Minimum : 16 h				
		Maximum : 7 d				
	The surface should be dry and free from any contamination prior to application of the subsequent coat.					
<b>Shelf Life</b>	18 months in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.					
<b>Heat Resistance</b>	Continuous	: 90°C(Non-immersion service)				
	Non-Continuous	: 120°C(Non-immersion service)				
<b>Chemical Resistance</b>		Acids	Alkalis	Solvents	Salts	Water
	Splash & Spillage	Good	Good	Good	Excellent	Excellent
	Fumes	Good	Very Good	Excellent	Excellent	Excellent
	Immersion	Fair	Fair	Good	Excellent	Excellent
<b>Standard Packing Unit</b>	12.8 kg base , 3.2 kg GITICURE 10050					
<b>Health and safety</b>	Do not store at temperature below 10 °C or above 30 °C. Protect skin and eyes from direct contact with liquid paint, and avoid prolonged breathing of solvent vapors. Use with adequate ventilation. Respiratory protection is recommended when applying this product in confined spaces or stagnant air.					
<b>Rev.05</b>	Mar. 2019					