



GITIDUR 32209

GITI ASSA Co.

Product Description	Two-pack quick drying acrylic polyurethane pigmented with aluminum with excellent color retention, and resistance against weathering.
Recommended Use	As a finish coat for use on the steel structures under or weathering conditions at chemical processing, petrochemical and marine industries.

Physical Properties

Finish and Color	Semi-Gloss, Silver			
Drying Time	Substrate Temperature	10 °C	25 °C	35 °C
	Set to touch ¹	1.5 h	1 h	30 min
	Dry through ¹	16 h	8 h	2 h
¹ Drying times are generally related to film thickness, air circulation, humidity, temperature, and number of coats, and will be affected correspondingly.				
Solids By Volume	45±2 % (Determined by ISO 3233)			
Theoretical Spreading Rate	9.0 m ² /L in 50 µm DFT			
Specific Gravity	1.10 ± 0.05 for Mixture of Base and Curing agent.			
Flash Point	Base: 17°C (Closed Cup) Curing agent: 8°C (Closed Cup)			

Application Details

Surface Preparation	Remove any oil, Grease, dirt and any other contaminants from the surface before painting by proper method such as solvent cleaning and fresh water washing, etc.
Application Conditions	The Surface should be clean and dry completely; The surface temperature should be min. 5 °C and at least 3 °C above the dew point of the air. In the confined spaces, provide adequate ventilation during application and drying.
Mixing	Base (Part A) : Curing Agent (Part B) 5 : 1 (by weight) Mix thoroughly together prior to application in the proportions with power agitator.
Pot Life	8 h at 25 °C
Preceding Coat	GITIZINC 11021, 11020, GITICOVER 23101, 23121, 24121, 23107, 23127, GITIMASTIC 52141, 51161
Thinning	Thinner No. 3021 Do not dilute each component separately, only the mixture.
Application Method	Spray (Airless or Air), Roller or Brush application. For airless spray application: Nozzle orifice : 0.015 ~ 0.017" Output pressure : 1800 ~ 2400 psi Spray angle : 40 ~ 60 ° (Airless spray data are indicative and subject to adjustment)



GITIDUR 32209

GITI ASSA Co.

Typical Film Thickness	50 µm DFT May be Specified in another film thickness than indicated depending on purpose and area of use.					
Recoating Interval	At 25 °C Minimum : 16 h Maximum : Free The surface should be dry and free from any contamination prior to application of the subsequent coat.					
Shelf Life	12 months in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.					
Heat Resistance	Continuous : 120 °C (Non-immersion service) Non-Continuous : 100 °C (Non-immersion service)					
Chemical Resistance		Acids	Alkalis	Solvents	Salts	Water
	Splash & Spillage	Fair	Fair	Fair	Excellent	Excellent
	Fumes	Good	Good	Good	Excellent	Excellent
Standard Packing Unit	16 kg base , 3.2 kg GITICURE 16037					
Health and safety	Do not store at temperature below 10 °C or above 30 °C. Protect skin and eyes from direct contact with liquid paint, and avoid prolonged breathing of solvent vapors. Use with adequate ventilation. Respiratory protection is recommended when applying this product in confined spaces or stagnant air.					
Rev.05	Mar. 2019					