



## GITILATEX 54431S

GITI ASSA Co.

<b>Product Description</b>	A standard PVA emulsion based latex paint with very good durability, workability, appearance and resistance to water.
<b>Recommended Use</b>	As an intermediate or finish coat for use on interior of buildings, it can be applied on the concrete, plaster, etc.

### Physical Properties

<b>Finish and Color</b>	Flat, White, Cream and other colors based on order
<b>Drying Time</b>	At 25 °C: 15 min. <sup>1</sup> Drying times are generally related to film thickness, air circulation, humidity, temperature and number of coats and will be affected correspondingly.
<b>Solids By Volume</b>	50 ± 2% (Determined by ISO 3233)
<b>Theoretical Spreading Rate</b>	10 m <sup>2</sup> /L at 50 μ DFT
<b>Specific Gravity</b>	1.50 ± 0.05
<b>Flash Point</b>	Non-Flammable

### Application Details

<b>Surface Preparation</b>	New concrete and plaster: remove laitance, dust and other contaminations from the surface with wire brush or sand paper. Maintenance and repair work: remove old paint and other contaminations from the surface, old cracked area should be sealed.
<b>Application Conditions</b>	The surface should be completely cleaned and dried. Do not apply when relative humidity is above 85% The surface temperature should be at least 3°C above dew point to prevent condensation.in confined areas, ventilate with clean air during application to assist solvent evaporation.
<b>Thinner</b>	Fresh water
<b>Application Method</b>	Spray (Airless or Air) ,Roller or brush application.
<b>Typical Film Thickness</b>	50 μ DFT



## **GITILATEX 54431S**

**GITI ASSA Co.**

<b>Recoating Interval (with others)</b>	At 25 °C	Minimum : 2 h
<b>Shelf Life</b>	24 months	
<b>Standard Packing Unit</b>	4.8 kg , 12 kg (plastic can)	
<b>Health and safety</b>	Do not store at temperature below 10°C or above 30°C. Protect skin and eyes from direct contact with liquid paint. Use with adequate ventilation. Respiratory protection is recommended when applying this product in confined spaces or stagnant air.	
<b>Rev:00</b>	May.2013	