



بسمه تعالی

خدمت جناب آقای مهندس رفیعیان
ریاست محترم بهره‌برداری امور خطوط لوله گاز اصفهان

موضوع: ارسال جواب آزمون رنگ بیس روم توربین هال

با سلام،

احتراماً: به پیوست سه برگ نتیجه آزمون پرایمر آلکید زینک کرومات و لایه
میانی آلکیدی و لایه رویه آلکیدی مربوط به بیس روم توربین هال جهت اطلاع و
در نظر گرفتن مراتب ارسال می‌گردد. ضمناً رنگهای فوق‌الذکر از نظر این واحد مورد
تأیید می‌باشند.

باتشکر

تقی قاکریان

رئیس آموزشگاه فنی اصفهان

رونوشت: ✓ شرکت محترم تامکار جهت اطلاع و اقدامات لازم

MPANY NAME : Gas Pipelines

SAMPLE RECEIVING DATE : SMPLE CODE :

RESULT ISSUING DATE : 18 / 12 / 1381 COATING TYPE : Alkyd intermediate coat

No	TEST TITLE	RESULT	ACCEPTABLE RANGE	DETAILS/ NOTES
1	COLOR	grey		
2	S.C. by weight	57%		
3	S.P. Gr .	1.35		
4	Dry to touch	$\frac{3}{4}$ hrs		
5	Dry hard	—		
6	D.F.T	—		
7	Theoretical coverage	—		
8	GLOSS	37		
9	Adhesion	5 B		
10	Hardness test	170		
11	Bending test	O.K.		
12	Impact test	O.K.		
13	Salt fog test	120 hrs		
14	Humidity test	120 hrs		
15	Temp . test			
16	Grind	25 μ		
17	Viscosity	130" cup4		

REMARKS : The results issued herein should not taken as permanent and unchanging
They correspond directly to the batch or lot represented by the sample submitted.

Note : This inetermediate coat is silitable for use

Tested by : R. Aghili 