



بسمه تعالی

خدمت جناب آقای مهندس رفیعیان

ریاست محترم بهره‌برداری امور خطوط لوله گاز اصفهان

موضوع: ارسال جواب آزمون رنگ بیس روم توربین هال

با سلام،

احتراماً: به پیوست سه برگ نتیجه آزمون پرایمر آلکید زینک کرومات و لایه  
میانی آلکیدی و لایه رویه آلکیدی مربوط به بیس روم توربین هال جهت اطلاع و  
در نظر گرفتن مراتب ارسال می‌گردد. ضمناً رنگهای فوق‌الذکر از نظر این واحد مورد  
تأیید می‌باشند.

باتشکر

تقی قاکریان

رئیس آموزشگاه فنی اصفهان

رونوشت: ✓ شرکت محترم تا مکار جهت اطلاع و اقدامات لازم

MPANY NAME : Gas Pipelines

SAMPLE RECEIVING DATE : ..... SMPLE CODE : .....

RESULT ISSUING DATE : 18 / 12 / 1381 COATING TYPE : Alkyd zinc chromate

Primer

No	TEST TITLE	RESULT	ACCEPTABLE RANGE	DETAILS/ NOTES
1	COLOR	Yellow		
2	S.C. by weight	67		
3	S.P. Gr .	1.40		
4	Dry to touch	$\frac{1}{2}$ hrs		
5	Dry hard	—		
6	D.F.T	—		
7	Theoretical coverage	—		
8	GLOSS	3		
9	Adhesion	4 B		
10	Hardness test	160		
11	Bending test	O.K.		
12	Impact test	O.K.		
13	Salt fog test	120 hrs		
14	Humidity test	120 hrs		
15	Temp . test	—		
16	Grind	35 $\mu$		
17	Viscosity	145" cup4		

**REMARKS** : The results issued herein should not taken as permanent and unchanging  
They correspond directly to the batch or lot represented by the sample submitted.

Note : This Primer is suitable for use .

Tested by : R. Aghili *Aghili*