

۱۸، ۸، ۸۱
تاریخ
شماره
پست
۸۱ / ۳۴۷



دانشگاه صنعت نفت
آموزشکد زنی. اصفهان

بسمه تعالی

بته: ریاست محترم بهره برداری امور خطوط لوله، گاز اصفهان

جناب آقای مهندس رفیعیان

موضوع: ارسال جواب آزمون

با سلام، احتراماً به پیوست سه برگ - جواب آزمون مربوط به پرایمر ایو کسی
زینک ریج و لایه میانی ایو کسی و لایه میانی کلرو کانسوچر جهت اطلاع و در نظر
گرفتن مراتب ارسال می گردد. ضمناً رونقهای فوق الذکر از نظر کاربرد یا مانع
می باشند.

پشتنکر
رفیعیان
تلفن فاکس: ۰۲۱-۸۱۲۳۰۰۰۰
تلفن: ۰۲۱-۸۱۲۳۰۰۰۰

COMPANY NAME : Gas pipe lines

SAMPLE RECEIVING DATE : SMPLE CODE :

RESULT ISSUING DATE : 15/8/1381 COATING TYPE : Epoxy zinc Rich primer

No	TEST TITLE	RESULT	ACCEPTABLE RANGE	DETAILS/ NOTES
1	COLOR	Dull grey		Recoating intervals : oc {Mini 10 hrs 10 {Max 72 hrs oc {Mini 8 hrs 15 {Max 60 hrs oc {Mini 6 hrs 20 {Max 48 hrs oc {Mini 4 hrs 25 {Max 36 hrs This primer must be recoated With Epoxy inter mediate . Avoid Applyat Rh above 80 y. Rainy weather
2	S.C. by weight	85		
3	S.P. Gr.	2.7		
4	Dry to touch	1 $\frac{1}{2}$ hrs		
5	Dry hard	7 days		
6	D.F.T			
7	Theoretical coverage			
8	GLOSS	20		
9	Adhesion	5 B		
10	Hardness test			
11	Bending test	OK		
12	Impact test	OK		
13	Salt fog	passed		
14	Humidity test	Passed		
15	Temp. test			
16	Grind	30 A		
17	Viscosity			

REMARKS : The results issued herein should not taken as permanent and unchanging
 They correspond directly to the batch or lot represented by the sample submitted.

Note : This primer is suitable for use .

Tested by : R. Aghili *Aghili*