



## GITIDUR 31211

GITI ASSA Co.

|                            |                                                                                                                                                                                                                                                                                                  |
|----------------------------|--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| <b>Product Description</b> | A two-pack high-build non-yellowing Polyurethane finish coat based on acrylic and aliphatic isocyanate with good resistance against splash and spillage of acids, alkalis, solvents, salts and water.<br>It has excellent gloss and color retention so provides long life time of exposed parts. |
| <b>Recommended Use</b>     | As a finish coat for use on steel or concrete structures under severe chemical or weathering corrosion condition at chemical processing, petrochemical and marine industries .                                                                                                                   |

### Physical Properties

|                                                                                                                                                                       |                                                                 |       |       |       |
|-----------------------------------------------------------------------------------------------------------------------------------------------------------------------|-----------------------------------------------------------------|-------|-------|-------|
| <b>Finish and Color</b>                                                                                                                                               | High Gloss, White ,Grey , Cream and other colors based on order |       |       |       |
| <b>Drying Time</b>                                                                                                                                                    | <b>Substrate Temperature</b>                                    | 10 °C | 25 °C | 35 °C |
|                                                                                                                                                                       | Set to touch <sup>1</sup>                                       | 4 h   | 2 h   | 1h    |
|                                                                                                                                                                       | Dry through <sup>1</sup>                                        | 48 h  | 8 h   | 2 h   |
| <sup>1</sup> Drying times are generally related to film thickness, air circulation, humidity, temperature, and number of coats, and will be affected correspondingly. |                                                                 |       |       |       |
| <b>Solids By Volume</b>                                                                                                                                               | 55±3 % (Determined by ISO 3233)                                 |       |       |       |
| <b>Theoretical Spreading Rate</b>                                                                                                                                     | 11 m <sup>2</sup> /L in 50 µm DFT                               |       |       |       |
| <b>Specific Gravity</b>                                                                                                                                               | 1.25±0.05 for mixture of base and curing agent.                 |       |       |       |
| <b>Flash Point</b>                                                                                                                                                    | Base: 14°c (Closed Cup)<br>Curing agent: 34°c (Closed Cup)      |       |       |       |

### Application Details

|                               |                                                                                                                                                                                                                                    |
|-------------------------------|------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|
| <b>Surface Preparation</b>    | Remove any oil, grease, dirt and any other contaminants from the surface before painting by proper method such as solvent cleaning and fresh water washing, etc.                                                                   |
| <b>Application Conditions</b> | The Surface should be clean and dry completely; The surface temperature should be min. 10 °C and at least 3 °C above the dew point of the air. In the confined spaces, provide adequate ventilation during application and drying. |
| <b>Mixing</b>                 | Base (Part A) : Curing Agent (Part B) = 8 : 1 (by weight)<br>Mix thoroughly together prior to application in the properties with power agitator.                                                                                   |
| <b>Pot Life</b>               | 8 h at 25 °C                                                                                                                                                                                                                       |
| <b>Preceding Coat</b>         | GITIZINC 11021, 11020, GITICOVER 23101, 23121, 24121, 23107, 23127, GITIMASTIC 43191, 52141, 51161                                                                                                                                 |
| <b>Thinning</b>               | Thinner No. 3021<br>Do not dilute each component separately, only the mixture.                                                                                                                                                     |



## **GITIDUR 31211**

**GITI ASSA Co.**

|                               |                                                                                                                                                                                                                                                                                                              |       |         |          |           |           |
|-------------------------------|--------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|-------|---------|----------|-----------|-----------|
| <b>Application Method</b>     | Spray (Airless or Air), Roller or Brush application<br>For airless spray application:<br>Nozzle orifice : 0.015" ~ 0.019"<br>Output pressure : 1800 ~ 2400 psi<br>Spray angle : 40 ~ 60°<br>(Airless spray data are indicative and subject to adjustment)                                                    |       |         |          |           |           |
| <b>Typical Film Thickness</b> | 50 ~ 75 µm DFT<br>May be specified in another film thickness than indicated depending on purpose and area of use.                                                                                                                                                                                            |       |         |          |           |           |
| <b>Recoating Interval</b>     | At 25 °C Minimum : 16 h<br>Maximum : Free<br>The surface should be dry and free from any contamination prior to application of the subsequent coat.                                                                                                                                                          |       |         |          |           |           |
| <b>Shelf Life</b>             | 12 months in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.                                                                                                                                                                           |       |         |          |           |           |
| <b>Heat Resistance</b>        | Continuous : 90 °C (Non-immersion service)<br>Non-continuous : 120 °C (Non-immersion service)                                                                                                                                                                                                                |       |         |          |           |           |
| <b>Chemical Resistance</b>    |                                                                                                                                                                                                                                                                                                              | Acids | Alkalis | Solvents | Salts     | Water     |
|                               | Splash & Spillage                                                                                                                                                                                                                                                                                            | Good  | Good    | Fair     | Excellent | Excellent |
|                               | Fumes                                                                                                                                                                                                                                                                                                        | Good  | Good    | Good     | Excellent | Excellent |
| <b>Standard Packing Unit</b>  | 16.8 kg base , 2.1 kg GITICURE 17075                                                                                                                                                                                                                                                                         |       |         |          |           |           |
| <b>Health and safety</b>      | Do not store at temperature below 10 °C or above 30 °C.<br>Protect skin and eyes from direct contact with liquid paint, and avoid prolonged breathing of solvent vapors. Use with adequate ventilation. Respiratory protection is recommended when applying this product in confined spaces or stagnant air. |       |         |          |           |           |
| <b>Rev.05</b>                 | Sept. 2020                                                                                                                                                                                                                                                                                                   |       |         |          |           |           |