

Yeolcoat QT604



Product Description A pure silicone and special synthetic resin based heat resistant paint containing inorganic pigments. After curing, the coating is very good resistant to thermal shock conditions from substrate temperature to 400 °C/752 °F, and provides excellent rust-preventing property.

Recommended Use As a heat resistant primer for use on stove, motor, boiler, heater, ship's engine, muffler, ventilator, steam lines and similar thermal implements operating from ambient temperature to 400 °C/752 °F.

Physical Properties

Finish and Color Flat. Silver (9180), Black (1999)

Drying Time	Substrate temperature	5 °C/41 °F	20 °C/68 °F	30 °C/86 °F
	Set to touch	4 h	1 h	30 m
	Dry to hard	24 h	10 h	8 h

* For full hardness, the coating should be exposed in service at temperature of 200°C/392°F over 1 hour time period.

Solids by Volume Silver : Approx. 27 %, Black : approx. 23 % (Determined by ISO 3233)

Theoretical Spreading Rate Silver : 14.0 m²/L, Black : 11 m²/L in 20 μm dry film thickness on a smooth surface.

Specific Gravity Approx. 1.12 ~ 1.27 according to color.

Flash Point 26 °C/79 °F (Closed cup)

Application Details

Surface Preparation Remove any oil grease, dirt and any other contaminants from the surface before painting by proper method such as solvent cleaning and fresh water washing, etc.
* Steel : Blast cleaning to Sa 2.5 or Power tool cleaning to St3, etc.

Application Conditions The surface should be completely cleaned and dried. Do not apply when relative humidity is above 85 %. The surface temperature should be at least 2.7 °C (5 °F) above dew point to prevent condensation. In confined areas, ventilate with clean air during application to assist solvent evaporation.

Preceding Coat May be applied directly to the well cleaned surface.
Yeolcoat Primer QP160 or according to specification.

Thinning Thinner No. 002 or 029K

This data is believed to be accurate but without any obligation

Please consult with our technical department for detail information . .

Yeolcoat QT604



Application Method	Spray (Airless or Air) or Brush application. For airless spray application ; Nozzle orifice : 330 μm ~ 381 μm (0.013" ~ 0.015") Output pressure : 11.7 MPa ~ 15.2 MPa Fan : 60 ° (Airless spray data are indicative and subject to adjustment)																		
Typical Film Thickness	20 ~ 25 μm dry. May be specified in another film thickness than indicated depending on purpose and area of use.																		
Recoating Interval	At 20 °C / 68 °F, Minimum : 1 h Maximum : Free Prior to overcoating, remove any oil, salts, chalking materials and any other contaminants on aged film completely by proper cleaning and/or fresh water washing.																		
Shelf Life	12 months																		
Heat Resistance	Continuous : 400 °C / 752 °F (Non-immersion service)																		
Chemical Resistance	<table border="1"> <thead> <tr> <th></th> <th>Acids</th> <th>Alkalis</th> <th>Solvents</th> <th>Salts</th> <th>Water</th> </tr> </thead> <tbody> <tr> <td>Splash & Spillage</td> <td>Good</td> <td>Fair</td> <td>Poor</td> <td>Excellent</td> <td>Excellent</td> </tr> <tr> <td>Fumes</td> <td>Excellent</td> <td>Excellent</td> <td>Good</td> <td>Excellent</td> <td>Excellent</td> </tr> </tbody> </table>		Acids	Alkalis	Solvents	Salts	Water	Splash & Spillage	Good	Fair	Poor	Excellent	Excellent	Fumes	Excellent	Excellent	Good	Excellent	Excellent
	Acids	Alkalis	Solvents	Salts	Water														
Splash & Spillage	Good	Fair	Poor	Excellent	Excellent														
Fumes	Excellent	Excellent	Good	Excellent	Excellent														
Standard Packing Unit	18 L, 4L																		
Remarks	The packing should be turned regularly twice a month to prevent the deposition. Avoid prolonged breathing of solvent vapors. Use with adequate ventilation. Respiratory protection is recommended during application in confined spaces or stagnant air. Keep away from sparks and open flames. Unduly heavy coat result in impaired adhesion. Although this product air dry rapidly, it remain somewhat soft until exposed to heat over 200 °C / 392 °F, and may be susceptible to mechanical damage. However, it is unaffected by moderate term weather exposure. Unduly heavy coat result in impaired adhesion. Keep the recommended dry film thickness.																		
Issued	August 2011																		

This data is believed to be accurated but without any obligation

Please consult with our technical department for detail information . .