



# GITIZINC 11020

GITI ASSA Co.

<b>Product Description</b>	Two-pack zinc rich polyamide epoxy primer with excellent protection of steel in sever corrosive environment that meets the compositional requirements based on SSPC Paint 20 level 1. (Min 85% zinc dust in dry film)
<b>Recommended Use</b>	As a zinc rich primer on blast cleaned steel in combination with advanced coating systems to improve protection against corrosion for protection of onshore & offshore structures.

## Physical Properties

<b>Finish and Color</b>	Matt, Grey			
<b>Drying Time</b>	<b>Substrate Temperature</b>	10 °C	25 °C	35 °C
	Set to touch <sup>1</sup>	1.5 h	1 h	30 min
	Dry Through <sup>1</sup>	12 h	8 h	2 h
<sup>1</sup> Drying times are generally related to film thickness, air circulation, humidity, temperature, and number of coats, and will be affected correspondingly.				
<b>Solids By Volume</b>	66 ± 3% (Determined by ISO 3233)			
<b>Theoretical Spreading Rate</b>	11.0 m <sup>2</sup> /L at 60 µm DFT.			
<b>Specific Gravity</b>	3.00 ± 0.1 for Mixture of Base and Curing agent.			
<b>Flash Point</b>	Base: 25°C (Closed Cup) Curing agent: 17°C (Closed Cup)			

## Application Details

<b>Surface Preparation</b>	Remove oil, grease, dirt and any other contaminants from the surface. The surface should be assessed and treated in accordance with ISO 8504. * Bare steel: Blast cleaning to Sa2.5 (ISO 8501-1:2007). Roughness: using suitable abrasive to achieve 50 ~ 75 µm (ISO 8503-2). * Shop primed steel: Clean, dry and undamaged approved shop primer. * Other surface: The coating may be used on the other substrates. Please contact GITI ASSA office for more information.
<b>Application Conditions</b>	The Surface should be clean and dry completely; The surface temperature should be min. 10 °C and at least 3 °C above the dew point of the air. In the confined spaces, provide adequate ventilation during application and drying.
<b>Mixing</b>	Base: Curing Agent = 12.5 : 1 (by weight) Mix thoroughly together half an hour prior to application in the properties as delivered.
<b>Pot Life</b>	8 h at 25 °C
<b>Thinning</b>	Thinner No. 3010 Do not dilute each component separately, only the mixture.



## **GITIZINC 11020**

**GITI ASSA Co.**

<b>Application Method</b>	Spray (Airless or Air), Roller or Brush application. For airless spray application ; Nozzle orifice : 0.017~0.019" Output pressure : 2100 ~ 2400 psi Spray angle : 40~60 ° (Airless spray data are indicative and subject to adjustment) During the application, continuous agitation is required to prevent the sedimentation of zinc powder. For Brush application: Use only for small areas or touch-up coating.					
<b>Typical Film Thickness</b>	60 ~ 75 µm DFT. May be Specified in another film thickness than indicated depending on purpose and area of use.					
<b>Recoating Interval</b>	At 20 °C Minimum : 16 h Maximum : 21 d The surface should be dry and free from any contamination prior to application of the subsequent coat.					
<b>Subsequent Coat</b>	GITINYL 53341, GITICR 23351, 31351, GITICOVER 23101, 23121, 24121, 23107, 23127, 31101, GITIMASTIC 43191, 52141, 51161, GITIGUARD 22121, 31121, GITIDUR 31201, 32201, 31211, 32211					
<b>Shelf Life</b>	12 months in a dry, cool, well ventilated space and away from source of heat and ignition. Containers must be kept tightly closed.					
<b>Heat Resistance</b>	120 °C (Non-immersion service)					
<b>Chemical Resistance</b>		Acids	Alkalis	Solvents	Salts	Water
	Splash & Spillage	Fair	Fair	Good	Excellent	Excellent
	Fumes	Good	Good	Excellent	Excellent	Excellent
<b>Standard Packing Unit</b>	32.5 kg base & 2.6 kg GITICURE 11050					
<b>Health and safety</b>	Do not store at temperature below 10 °C or above 30 °C. Protect skin and eyes from direct contact with liquid paint, and avoid prolonged breathing of solvent vapors. Use with adequate ventilation. Respiratory protection is recommended when applying this product in confined spaces or stagnant air.					
<b>Rev.09</b>	Oct. 2022					